

Selection Rule in Josephson Coupling between In and Sr_2RuO_4

R. Jin, Y. Liu*

Department of Physics, The Pennsylvania State University, University Park, PA 16802, USA

Z. Q. Mao, Y. Maeno

Department of Physics, Kyoto University, Kyoto 606-8502, Japan

CREST, Japan Science and Technology Corporation, Kawaguchi, Saitama 332-0012, Japan

(February 1, 2008)

We have studied the Josephson coupling between a conventional s -wave superconductor (In) and Sr_2RuO_4 and found that the coupling is allowed in the in-plane direction, but not along the c axis. This selection rule indicates that the symmetry of superconducting order parameter of Sr_2RuO_4 is either p - or alternatively, purely d -wave. If Sr_2RuO_4 is a p -wave superconductor, as strongly favored by other experimental evidence, our result suggests that the pairing state of Sr_2RuO_4 is Γ_5^- with $\mathbf{d}(\mathbf{k}) = \mathbf{z}(k_x \pm ik_y)$, a nodeless state in which the spins of the superconducting electrons lie in the RuO_2 planes.

74.50.+r, 74.25.Fy, 74.70.-b

Recently, the first known Cu-free layered perovskite superconductor, Sr_2RuO_4 [1], has emerged as a new focus of superconducting materials research. The main issue is whether the pairing symmetry of Sr_2RuO_4 is spin triplet with odd parity (p -wave) as predicted theoretically [2]. A growing body of experimental evidence, including results obtained from muon spin relaxation [3], NMR $1/T_1$ and Knight shift [4], neutron scattering [5], impurity effect [6], proximity Josephson coupling effect [7], and specific heat [8] measurements, has shown that the pairing symmetry is unconventional, most likely p -wave. In particular, the flat Knight shift observed across the T_c of Sr_2RuO_4 may be considered as direct evidence for the p -wave pairing state in Sr_2RuO_4 [4] (see below). In addition to the only known p -wave superconductor, ^3He , certain heavy-fermion compounds are also possible candidates for p -wave superconductors. However, Sr_2RuO_4 has an advantage that its electronic band structure is considerably simpler than those of heavy-fermion compounds, making it perhaps a more tractable material for demonstrating a p -wave pairing state.

Assuming a weak spin-orbit coupling, five possible p -wave states are allowed by the crystal symmetry of Sr_2RuO_4 [2]. Among them, the Γ_5^- state, with the $\mathbf{d}$ -vector given by $\mathbf{d}(\mathbf{k}) = \mathbf{z}(k_x \pm ik_y)$ ($\mathbf{z}$ denotes the unit vector along the c axis), is favored by muon spin relaxation [3] and NMR Knight shift [4] results. The physical meaning of $\mathbf{d}$ -vector is as follows. The magnitude of the $\mathbf{d}$ -vector is the amplitude of the superconducting order parameter. When projected to the direction of the $\mathbf{d}$ -vector, the component of total superconducting electron spins is zero. The Γ_5^- state for Sr_2RuO_4 is nodeless with all spins of the superconducting electrons lying in the RuO_2 planes. Our experiment on Josephson coupling between an s -wave superconductor, In, and Sr_2RuO_4 along different crystalline orientations, is shown schematically in Fig. 1. This experiment can be used to

determine which pairing state within the p -wave scenario is adopted by Sr_2RuO_4 . In this Letter, we present our experimental finding of a selection rule in the Josephson coupling between In and Sr_2RuO_4 . It was found that this coupling is allowed in the in-plane direction (Fig. 1a) but not along the c axis (Fig. 1b). If Sr_2RuO_4 is a spin-triplet superconductor, as strongly favored by other experimental results, our observation provides *direct* experimental evidence that the pairing state of Sr_2RuO_4 is indeed Γ_5^- . In the context of the spin-singlet d -wave scenario [9], which is not inconsistent with our selection rule but contradicts the NMR Knight shift result [4], the present work suggests that the pairing state in Sr_2RuO_4 is purely d -wave.

Single crystals of Sr_2RuO_4 were grown by a floating-zone method using an image furnace [1]. Results from *a.c.* magnetic susceptibility measurements showed a superconducting transition at $T = T_c = 1.45$ K (onset) and a transition width around 0.05 K for crystals prepared in two separate growth runs. Its superconducting coherence lengths at zero temperature are $\xi_{ab} = 660$ Å and $\xi_c = 33$ Å for the in-plane and c -axis directions, respectively [10]. To prepare c -axis In/ Sr_2RuO_4 junctions, a Sr_2RuO_4 single crystal was cleaved along the ab -plane. Atomic force microscope (AFM) studies of the cleaved surface show an atomically flat surface over an area of up to $(10 \mu\text{m})^2$. A freshly cut In wire of 0.25 mm in diameter was pressed on the crystal immediately after it was cleaved. The in-plane junctions were prepared on Sr_2RuO_4 single crystals with a finely polished ac face. AFM imaging showed that the polished face is fairly rough with micron-size mechanical damage. To our knowledge, no chemical solution can etch Sr_2RuO_4 to obtain a smooth surface. Thus, the freshly cut In wire was directly pressed on clean, but as-polished ac face of Sr_2RuO_4 to form an in-plane junction. For both types of junctions, the junction area is $\sim 0.05 \text{ mm}^2$ with junction

resistances ranging from 0.1 to 100 Ω . Electrical measurements were carried out in *d.c.* in a ^3He cryostat with a base temperature of 0.3 K. A μ -metal box shielded the samples from residual magnetic field.

In Fig. 2, the I-V curves of an in-plane In/Sr₂RuO₄ junction (Sample #11) are shown. In this case, the current (I) flows along the in-plane direction. A non-zero supercurrent, followed by a linear I-V characteristic, was evident. Qualitatively the same behaviors have been found in four other in-plane junctions with non-zero critical current I_c . The temperature dependence of I_c , shown in Fig. 3 for Samples #11 and #12, has the general shape of that for a superconductor-normal metal-superconductor (SNS') junction [11]. The magnetic field dependence of I_c was measured for one in-plane junction (without μ -metal shield). While I_c was found to decrease with increasing field, no Fraunhofer pattern was observed, suggesting that the junction is not very uniform. For two dissimilar *s*-wave superconductors, the Ambegaokar-Baratoff (A-B) limit for $I_c R_N$ is given by $I_c R_N \leq (\Delta_1/e)K\{[1 - (\Delta_1/\Delta_2)^2]^{1/2}\}$, where R_N is junction resistance in the normal state, Δ_1 and Δ_2 are zero-temperature energy gaps for two superconductors, and the function K is the elliptic integral of the first kind [12]. Unfortunately, the gap for Sr₂RuO₄ is yet to be determined experimentally [13]. However, if one estimates the gap using the BCS result, $\Delta = 1.764k_B T_c \approx 0.22$ meV, this leads to an A-B limit of 0.6 mV. At $T = 0.3$ K, values of $I_c R_N$ are 0.16 and 0.18 mV for Junctions #11 and #12, and 15, 16, and 45 μV for three other (in-plane) samples, respectively. The numbers for Junctions #11 and #12 are a substantial fraction of the A-B limit, suggesting that, at least for these two junctions, the observed I_c is due to a finite Josephson coupling between In and Sr₂RuO₄ in the in-plane direction.

In *c*-axis In/Sr₂RuO₄ junctions, no finite supercurrent was found. While it is not clear why a natural barrier is easier to form in *c*-axis junctions, experimentally most *c*-axis junctions were found to exhibit tunneling behavior. In principle, it is possible that the presence of a tunnel barrier suppresses the amplitude of the superconducting order parameter [14], resulting in a vanishing supercurrent, independent of the pairing symmetry of Sr₂RuO₄. In two *c*-axis In/Sr₂RuO₄ junctions, however, instead of tunneling features, an excess current (I_0) or zero-bias conductance peak (Fig. 4) was seen. The excess current or zero-bias conductance peak is a signature of the Andreev reflection process at a normal metal-superconductor (N-S) interface, where an incoming normal electron with energy below the gap of the superconductor combines with another electron to form a Cooper pair which enters the superconductor. As a result, a hole is reflected, giving rise to "extra" charge passing through the interface. Since the Andreev reflection occurs only at a metallic interface, its presence above the T_c of Sr₂RuO₄ indicates that the interface between In and Sr₂RuO₄ is

metallic in nature. This excess current was seen to persist below the T_c of Sr₂RuO₄, which may be explained by the existence of a normal layer at the *ab* face of the Sr₂RuO₄ crystal. This is further supported by the observation that no gap features associated with Sr₂RuO₄ were present below the T_c of Sr₂RuO₄ in all *c*-axis tunnel junctions we have studied [13]. Although the precise origin of this normal layer is unknown, it may be due to mechanical stress and/or oxygen deficiency near the crystal surface. No supercurrent was observed down to 0.38 and 0.65 K respectively in either of these two *c*-axis junctions showing Andreev reflection, suggesting that no Josephson coupling was established in these *c*-axis junctions.

An important question is whether the lack of finite Josephson coupling between In and Sr₂RuO₄ along the *c* axis is of an intrinsic or extrinsic origin. In addition to a metallic contact between In and the normal top layer of Sr₂RuO₄, the interface between the normal layer and the bulk superconducting Sr₂RuO₄ should be metallic as well since it is naturally formed with no oxygen deficiency or mechanical stress expected. As a result, the two *c*-axis In/Sr₂RuO₄ junctions showing Andreev reflection should be SNS' junctions with two metallic interfaces. If Sr₂RuO₄ is an *s*-wave superconductor, Josephson coupling should be possible in these *c*-axis junctions as long as the thickness of the N-layer is within a few times of the normal coherence length ξ_N [11]. In the clean limit, which we believe is appropriate for Sr₂RuO₄, $\xi_N = \hbar v_N / (2\pi k_B T)$, where v_N is the Fermi velocity. Using $v_N = 1.4 \times 10^6$ cm/s along the *c* axis [15], we have $\xi_N = 774$ Å for Sr₂RuO₄ at $T = 0.38$ K, the lowest temperature measured for Sample #17. Compared with the distance between two adjacent RuO₂ layers, 6.4 Å, a length a few times of ξ_N would be of a few hundreds of the inter-layer distance. It is very unlikely that the normal layer formed at a freshly cleaved Sr₂RuO₄ single crystal can be so thick. Therefore the absence of supercurrent in *c*-axis In/Sr₂RuO₄ junctions cannot be due to an overly thick N-layer.

Is it possible that the supercurrent is too small to be measured for these *c*-axis junctions? If the A-B limit for $I_c R_N$ (0.6 mV) is a good guide, we expect a critical current on the order of 100 μA for Sample #17 with $R_N = 5.7$ Ω . Even using the experimental values of $I_c R_N$ for two in-plane In/Sr₂RuO₄ junctions shown in Fig. 3 (0.16 and 0.18 mV respectively at 0.3 K), we still expect $I_c > 28$ μA , well above our measurement limit. For another *c*-axis junction which also showed Andreev reflection features, $R_N = 0.22$ Ω , we should expect an even larger supercurrent. Therefore, the absence of Josephson coupling between In and Sr₂RuO₄ along *c* axis must be due to intrinsic reasons, probably a spin-triplet pairing state in Sr₂RuO₄. It should be noted that, unlike experiments on *c*-axis tunneling between Pb and high- T_c superconductors [16,17], we are attempting to demonstrate the

absence, not the presence, of a c -axis Josephson coupling between the two superconductors. Hence, whether or not the in-plane tunneling due to the presence of steps on the cleaved ab face may be present in our c -axis junctions is not an issue since the presence of the in-plane coupling will only help give rise to a finite I_c .

The absence of Josephson coupling between a spin-singlet (even-parity) and a spin-triplet (odd-parity) superconductor was first proposed as a test for the unconventional pairing state in heavy-fermion superconductors [18]. However, it was subsequently pointed out that the first order Josephson coupling between two superconductors with different parities was possible through spin-orbit coupling [19]. In the presence of the spin-orbit coupling, the Cooper pairs of different parities will be mixed at the interface between the s - and the p -wave superconductor, resulting in a direct Josephson coupling between them. In fact, it has been shown that I_c can be written as [20]

$$I_c = 2e \text{Im} \int \lambda T_t^2 F^* K(\mathbf{x}) [(\mathbf{d}(\mathbf{k}, \mathbf{x}) \times \mathbf{k}) \cdot \mathbf{n}] d\mathbf{x} d\mathbf{k} \quad (1)$$

where λ is a dimensionless parameter, T_t the tunneling matrix, F^* the Gor'kov function, K the kernel and $\mathbf{n}$ the unit vector normal to the interface. In Eq. 1, $\mathbf{x}$ and $\mathbf{k}$ are real- and momentum-space coordinates, and the integration is carried out over the junction interface and the Fermi surface of the p -wave superconductor. The physical origin of Eq. 1 can be easily understood if we rewrite $[(\mathbf{d}(\mathbf{k}, \mathbf{x}) \times \mathbf{k}) \cdot \mathbf{n}]$ as $[\mathbf{d}(\mathbf{k}, \mathbf{x}) \cdot (\mathbf{k} \times \mathbf{n})]$. Since $\mathbf{d}$ and $\mathbf{k} \times \mathbf{n}$ represent essentially the spin and the orbital angular momentum of the superconducting condensate at the interface, respectively, $[\mathbf{d}(\mathbf{k}, \mathbf{x}) \cdot (\mathbf{k} \times \mathbf{n})]$ merely reflects the spin-orbit coupling strength of the p -wave superconductor, which gives rise to the (orientation-dependent) Josephson coupling between the p - and the s -wave superconductor as mentioned above. If the pairing symmetry in Sr_2RuO_4 is indeed p -wave, Eq. 1 implies that the Josephson coupling between In and Sr_2RuO_4 is orientation-dependent. In particular, among five possible representations (Γ_{1-5}^-) [2], Eq. 1 states that, for in-plane junctions, $I_c \neq 0$ only if the pairing state of Sr_2RuO_4 is Γ_5^- with $\mathbf{d}(\mathbf{k}) = \mathbf{z}(k_x \pm ik_y)$.

The above result is consistent with *all other* experimental findings obtained thus far. In particular, in the NMR experiment [4], the electron spin susceptibility of Sr_2RuO_4 was found to be a constant within experimental error as temperature was brought from above T_c to 15 mK, as expected for the Γ_5^- state. While the standard theory predicts exponentially small electron spin susceptibility in the zero-temperature limit for s -wave superconductors [21], it was found that Hg [22] and Sn [23] showed finite electron spin susceptibility well below T_c . This was explained [24] by the presence of spin-orbit coupling within an s -wave picture. Nevertheless, a finite drop in electron spin susceptibility was still observed

across T_c for both Hg [22] and Sn [23]. A constant electron spin susceptibility (or Knight shift) in Sr_2RuO_4 containing relatively light elements (corresponding to weak spin-orbit coupling) is difficult to be explained within a spin-singlet picture.

It should be pointed out that a d -wave scenario has recently been proposed for Sr_2RuO_4 [9]. This scenario contradicts the NMR Knight shift result. However, if it turns out to be true, the result of the present work suggests that the superconducting order parameter in Sr_2RuO_4 is purely d -wave. Given that the issue of whether the pairing symmetry in high- T_c cuprates is purely d -wave is still being debated, our selection rule result would be of significance in that context as well.

In conclusion, we have found a selection rule in the Josephson coupling between In and Sr_2RuO_4 . While a phase sensitive experiment may ultimately be required to settle this issue, the totality of the available results on Sr_2RuO_4 , and the remarkable consistency among them, makes a compelling case for a p -wave pairing state in Sr_2RuO_4 . In this context, the present work shows that the pairing state of Sr_2RuO_4 is Γ_5^- .

We would like to acknowledge helpful discussions with D.F. Agterberg, A.J. Millis, T.-L. Ho, J. Sauls, and C.C. Tsuei, and particularly M. Sigrist who has brought our attention to Eq. 1. This work is supported in the US In part by NSF through grants DMR-9702661, DMR-9974327, and ECS-9705839.

* To whom correspondence should be addressed.

- [1] Y. Maeno *et al.*, Nature **372**, 532 (1994).
- [2] T.M. Rice and M. Sigrist, J. Phys.: Cond. Matt. **7**, L643 (1995).
- [3] G.M. Luke *et al.*, Nature **394**, 558 (1998).
- [4] K. Ishida *et al.*, Nature **396**, 658 (1998).
- [5] T.M. Riseman *et al.*, Nature **396**, 242 (1998).
- [6] A.P. Mackenzie *et al.*, Phys. Rev. Lett. **80**, 161 (1998).
- [7] R. Jin *et al.*, Phys. Rev. B **59**, 4433 (1999).
- [8] S. Nishizaki *et al.*, J. Phys. Soc. Jpn. **67**, 560 (1998).
- [9] I.I. Mazin and D.J. Singh, Phys. Rev. Lett. **82**, 4324 (1999).
- [10] T. Akima, S. Nishizaki, and Y. Maeno, J. Phys. Soc. Japan **68**, 694 (1999).
- [11] K.A. Delin and A.W. Kleinsasser, Supercond. Sci. Technol. **9**, 227 (1996).
- [12] V. Ambegaokar and A. Baratoff, Phys. Rev. Lett. **10**, 486 (1963); erratum, **11**, 104 (1963).
- [13] R. Jin *et al.*, to be published.
- [14] A.W. Kleinsasser *et al.*, Appl. Phys. Lett. **57**, 1811 (1990).
- [15] T. Oguchi, Phys. Rev. B **51**, 1385 (1995); D.J. Singh, *ibid* **52**, 1358 (1995).
- [16] A.G. Sun *et al.*, Phys. Rev. Lett. **72**, 2267 (1994); Phys.

- Rev. B **54**, 6734 (1996).
- [17] R. Kleiner *et al.*, Phys. Rev. Lett. **76**, 2161 (1996); K.A. Kouznetsov *et al.*, *ibid* **79**, 3050 (1997).
 - [18] J.A. Pals, W. van Haeringen, and M.H. van Maaren, Phys. Rev. B **15**, 2592 (1977).
 - [19] E.W. Fenton, Solid State Comm. **54**, 709 (1985).
 - [20] V.B. Geshkenbein and A.I. Larkin, JETP Lett. **43**, 395 (1986).
 - [21] K. Yosida, Phys. Rev. **110**, 769 (1958).
 - [22] F. Reif, Phys. Rev. **106**, 208 (1957)
 - [23] G.M. Androes and W.D. Knight, Phys. Rev. Lett. **2**, 386 (1959).
 - [24] R.A. Ferrell, Phys. Rev. Lett. **3**, 262 (1959); P.W. Anderson, *ibid* **3**, 325 (1959).

FIG. 1. Schematics of (a) in-plane and (b) *c*-axis In/Sr₂RuO₄ junctions.

FIG. 2. I-V curves at various temperatures for an In-plane In/Sr₂RuO₄ junction (Sample #11). Finite critical current I_c is indicated.

FIG. 3. Temperature dependence of the critical current, $I_c(T)$, for two in-plane In/Sr₂RuO₄ junctions (samples #11 and #12).

FIG. 4. a) I-V curves for a *c*-axis In/Sr₂RuO₄ Junction (Sample #17); b) Dynamic conductance of the same junction.

This figure "Fig.1.gif" is available in "gif" format from:

<http://arXiv.org/ps/cond-mat/9909214v1>

This figure "Fig.2.gif" is available in "gif" format from:

<http://arXiv.org/ps/cond-mat/9909214v1>

This figure "Fig.3.gif" is available in "gif" format from:

<http://arXiv.org/ps/cond-mat/9909214v1>

This figure "Fig.4.gif" is available in "gif" format from:

<http://arXiv.org/ps/cond-mat/9909214v1>